

Cost is
Long forgotten
but
Quality is
remembered
forever...



GOYAL RESINS & POLYMERS
MANUFACTURER OF ALL TYPES OF ALKYD RESIN

414/5, Khatipura, Sukhliya Gram, Link Road, INDORE-10
Ph. : 0731-4023744, 2904121
Mobile : 94250-82512, 98931-55050
Email : goyalresins@yahoo.com

Designed at Profile@0731-261632

we
DELIVER
what we
PROMISE



TECHNICAL SPECIFICATION



GOYAL RESINS & POLYMERS

Product Code	Solid Content	Acid Value	Viscosity At 30 C in FCB/4	Type Of Oil	Oil %	Pthaliec %	Suggested Use
LONG OIL ALKYD							
18633	99 +-1	12	90 +-10 in 50%MTO	ARLO	58	25	1st Quality Superior Enamel Paint
2931	99 +-1	12	90 +-10 in 50%MTO	ARLO	60	25	1st Quality Paint
1063	99 +-1	12	60 +-10 in 50% MTO	LINSEED	63	24	For Good Glossy Paint and printing inks
1064	99 +-1	12	110 +-10 in 50%MTO	LINSEED	64	24	For Good Glossy Paint and printing inks
2064	99 +-1	12	120 +-10 in 50%MTO	D.C.O	64	22	For paint, primer and distemper
2060	99 +-1	12	100 +-10 in 50%MTO	D.C.O	60	24	For paint, primer and distemper
3060	99 +-1	10	90 +-10 in 50%MTO	SOYA	60	25	For Light Colour and White Paint
VARNISH ALKYD							
1152	70 +-2	15	250 +-10 in 40%MTO	LINSEED	52	33	For Primer's and Varnishes
2252	70 +-2	15	250 +-10 in 40%MTO	D.C.O	52	33	For Primer's and Varnishes
Also Available In 80%							
MEDIUM OIL ALKYD							
1153	70 +-2	15	120 +- in 40%MTO	LINSEED	52	33	For Good Quality Paints
2253	70 +-2	15	130 +- in 40%MTO	D.C.O	52	33	For Good Quality Paints
SHORT OIL ROSIN MODIFIED							
A1543	70 +-2	25	130 +-10 in 40%MTO	ARLO	42	25	1st quality furniture enamals paints
1543	70 +-2	25	130 +-10 in 40%MTO	LINSEED	42	25	For furniture enamals paints
2543	70 +-2	20	140 +-10 in 40%MTO	D.C.O	42	25	For furniture enamals paints
FAST DRYING ALKYD							
3236	70 +-2	15	130 +-10 in 40% MTO	SOFA	36	25	For Automative and fast drying enamel
3232	70 +-2	15	130 +-10 in 40% MTO	SOFA	32	27	For Automative and fast drying enamel

HARD RESIN

Product Code	Softing Pot.	Acid Value	Viscosity At 30 C in S.T.	T in MTO	Col of 50% Soln.	Suggested Use
PHENOL MODIFIED - ROSIN DERIVATIVES						
5003	140-150	25	40 +-10	1:02	12 MAX.	For Printing inks
MALIEC MODIFIED - ROSIN DERIVATIVES						
5011	130-135	20	27 +-3	1:05	12 MAX.	For improve gloss in paint

MALIEC SOLUTION

SOLUTION

Product Code	Solid Content	Acid value	Viscosity At 30 C in FCB/4	Solvent	Suggested Use
5011	70 +-2	12 to 15	27 +-3	Xyline/MTO	For improve gloss (ready mix Solution)
HAMMERTONE SOLUTION					
1011	80 +-2	12 to 15	25 +-5 in 50% Xyline	Xyline	For Hammertone finish